

**PATENT APPLICATION**  
**Attorney Docket No.: D/A0438**

**APPLICATION FOR**  
**UNITED STATES LETTERS PATENT**

**TO ALL WHOM IT MAY CONCERN:**

**Be it known that WE, Sean X. Pan, Mark S. Thomas, and Mark C. Petropoulos,**  
**have invented a**

**SUBSTRATE WITH EXTERNAL MEMBER**

**SUBSTRATE WITH EXTERNAL MEMBER**

**BACKGROUND OF THE INVENTION**

When a photoreceptor is dip coated, the layer thickness increases slowly to a target value after the takeup speed reaches a constant value. The resulting non-uniformity in layer thickness is called "sloping." "Sloping" of the deposited layer over the imaging area of the photoreceptor is undesirable since it can degrade the performance of the photoreceptor. To prevent the deposited layer from exhibiting "sloping" in the imaging area, one can use a longer substrate to provide a longer non-imaging area so that the "sloping" of the deposited layer occurs only in the non-imaging area while the deposited layer exhibits relatively uniform thickness in the imaging area. However, a longer substrate and a longer non-imaging area increase costs since more materials have to be used in the substrate and the deposited layer or layers. Thus, there is a need, which the present invention addresses, for new methods to eliminate or reduce the above described problem.

Coating methods and apparatus are described in Petropoulos et al., U.S. Patent 5,633,046; Herbert et al., U.S. Patent 5,683,742; Swain et al., U.S. Patent 6,132,810; Petropoulos et al., U.S. Patent 5,578,410; and Crump et al., U.S. Patent 5,385,759.

**SUMMARY OF THE INVENTION**

The present invention is accomplished in embodiments by providing an apparatus comprising:

(a) a substrate including a level intermediate region disposed between a first end region and a second end region;

(b) a first external member disposed circumferentially around the first end region in a continuous manner and protruding above the level intermediate region, thereby resulting in a deposition region including the surface of the first external member covering the first end region, an optional exposed first end region portion, and the intermediate region; and

1 (c) a dip coated layer over the entire deposition region, wherein the portion of the  
2 dip coated layer over the first external member and the optional exposed first end  
3 region portion is formed prior to the portion of the dip coated layer over the  
4 intermediate layer.

5 There is also provided in embodiments an apparatus comprising:

6 (a) a substrate defining a longitudinal axis and including a level intermediate  
7 region disposed between a first end region and a second end region;

8 (b) a plurality of external members, each of the external members protruding  
9 above the level intermediate region and disposed only partially around the first end  
10 region, wherein the plurality of the external members, when viewed at a substrate end  
11 view, collectively extend circumferentially around the first end region in a continuous  
12 manner, thereby resulting in a deposition region including the surfaces of the external  
13 members covering the first end region, an optional exposed first end region portion,  
14 and the intermediate region; and

15 (c) a dip coated layer over the entire deposition region, wherein the portion of  
16 the dip coated layer over the external members and the optional exposed first end  
17 region portion is formed prior to the portion of the dip coated layer over the  
18 intermediate layer.

19 In additional embodiments, there is provided a coating method comprising:

20 (a) providing an apparatus including:

21 (i) a substrate including a level intermediate region disposed between a first end  
22 region and a second end region;

23 (ii) a first external member disposed circumferentially around the first end  
24 region in a continuous manner and protruding above the level intermediate region,  
25 thereby resulting in a deposition region including the surface of the first external  
26 member covering the first end region, an optional exposed first end region portion, and  
27 the intermediate region; and

28 (b) dip coating a layer of a coating solution over the entire deposition region,  
29 wherein the portion of the dip coated layer over the first external member and the  
30 optional exposed first end region portion is formed prior to the portion of the dip  
31 coated layer over the intermediate layer.

## 32 **BRIEF DESCRIPTION OF THE DRAWINGS**

FIG. 1 is an elevational view of a first embodiment of the present coated substrate;

FIG. 2 is an elevational view of a second embodiment of the substrate useful in the present invention;

FIG. 3 is an elevational view of a third embodiment of the substrate useful in the present invention;

FIG. 4 is an elevational view of a fourth embodiment of the substrate useful in the present invention;

FIG. 5 is an elevational view of a fifth embodiment of the substrate useful in the present invention; and

FIG. 6 is an end view of the substrate depicted in FIG. 5.

Unless otherwise noted, the same reference numeral in different Figures refers to the same or similar feature.

### **DETAILED DESCRIPTION**

As used herein, the phrase “coating solution” encompasses any fluid composition including the liquid medium and the coating material regardless of the extent that the coating material may be dissolved in the liquid medium.

As seen in the Figures, the substrate (2A, 2B, 2C, 2D, 2E), having a longitudinal axis X, includes an optional uncoated region (8A, 8B, 8C, 8D) and an intermediate region (10A, 10B, 10C, 10D, 10E) disposed between a first end region (12A, 12B, 12C, 12D, 12E) and a second end region (14A, 14B, 14C, 14D, 14E). In embodiments where the substrate is part of an electrostatographic imaging member (e.g., a photoreceptor), one or more of the first end region, the second end region, and the optionally uncoated region may correspond to a non-imaging area of the imaging member, whereas the imaging area of the imaging member includes at least the intermediate region and optionally one or both of the first end region and the second end region. In embodiments, the first end region, the second end region, and the optional uncoated region correspond to the non-imaging area of the imaging member, and the intermediate region corresponds to the imaging area. A deposition region (6A, 6B, 6C, 6D, 6E) includes the intermediate region, the surface of external member or members (18A-E, 19D-E, 20A-D) covering the first end region and the second end region, and any optional exposed portion of the first end region and the second end region not covered by the external member or members.

1 As used herein, the term "external" as in "external member" indicates that the  
2 member is a separately created component which is moved into position onto the  
3 substrate surface, i.e., the external member is not a surface feature created from the  
4 substrate.

5 In FIG. 1, the first end region 12A includes a first external member 18A which  
6 is depicted as a single band having a rectangular shape when viewed in cross section  
7 along the longitudinal axis that is disposed circumferentially around the first end region  
8 in a continuous manner. The second end region 14A optionally includes a second  
9 external member 20A similar or dissimilar to the first external member. In FIG. 1, the  
10 second external member 20A is depicted as a single band having a rectangular shape  
11 when viewed in cross section along the longitudinal axis that is disposed  
12 circumferentially around the second end region in a continuous manner. In FIG. 1, a  
13 dip coated layer 16 is formed over the entire deposition region.

14 In FIG. 2, the first external member 18B is depicted as a single band having an  
15 elongated rectangular shape when viewed in cross section along the longitudinal axis  
16 that is disposed circumferentially around the first end region 12B and the uncoated  
17 region 8B in a continuous manner. In FIG. 2, the second external member 20B is  
18 depicted as a single band having a rectangular shape when viewed in cross section  
19 along the longitudinal axis that is disposed circumferentially around the second end  
20 region in a continuous manner.

21 In FIG. 3, the first external member 18C and the second external member 20C are  
22 depicted as wires (having a circular shape when viewed in cross section along the  
23 longitudinal axis) that are disposed circumferentially around the respective first end  
24 region and the second end region in a continuous manner. The wires may be wrapped  
25 one time or several times around the first end region and the second end region.

26 In FIG. 4, the first end region 12D includes a plurality of external members (18D,  
27 19D), each external member is disposed circumferentially around the first end region in  
28 a continuous manner. Each external member (18D, 19D) is depicted as having a  
29 triangular shape when viewed in cross section along the longitudinal axis. The  
30 plurality of external members in the first end region may range in number for example  
31 from 2 to 5. The plurality of external members may be arranged in any suitable manner  
32 with respect to one another such as regular or irregular spacing and parallel or non-  
33 parallel arrangement. Moreover, each of the plurality of external members may be the  
34 same or different from one another in shape, surface height, size, and the like. The  
35 optional second external member 20D is depicted as a single band (having a triangular

1 shape when viewed in cross section along the longitudinal axis) disposed  
2 circumferentially around the second end region in a continuous manner. In FIG. 4, the  
3 portions of the first end region 12D and the second end region 14D not covered by the  
4 external members are depicted as tapered surfaces.

5 FIGS. 5-6 depict on the first end region 12E a plurality of external members  
6 (18E, 19E), each external member is disposed only partially around the first end region,  
7 wherein the plurality of the external members (18E, 19E), when viewed at a substrate  
8 end view, collectively extend circumferentially around the first end region in a  
9 continuous manner (also referred herein as "partial external members"). The plurality  
10 of partial external members may range in number from 2 to 5. The partial external  
11 members may be spaced at regular or irregular intervals (along the longitudinal axis) at  
12 a spacing ranging from 0 to about 1 cm, and particularly from about 1 mm to about 5  
13 mm. In FIGS. 5-6, there are absent an uncoated region and any external member on the  
14 second end region.

15 In embodiments of the present invention, each external member protrudes above  
16 the level intermediate region by a value ranging for example from about 10  
17 micrometers to about 10 mm, and particularly from about 0.5 mm to about 5 mm. Each  
18 external member may have a width (i.e., along the longitudinal axis) ranging for  
19 example from about 10 micrometers to about 100 mm, and particularly from about 0.5  
20 mm to about 20 mm. Moreover, when viewed in cross section along the longitudinal  
21 axis, each external member may have any suitable shape such as circular, triangular  
22 (e.g., isosceles, equilateral, right, and obtuse), square, rectangular, half circle, and the  
23 like. The top surface of each external member when viewed in cross section along the  
24 longitudinal axis may be a straight line parallel to the longitudinal axis, a tapered line, a  
25 curved line, a peak, a series of steps, and the like. The external member or members  
26 may occupy a part of or all of the first end region. The external member or members  
27 may occupy a part of or all of the second end region. Different types of external  
28 members may be used. By disposing the external member or members  
29 circumferentially around one or both end regions in a continuous manner, the  
30 likelihood is eliminated or minimized that the coating solution will bypass the external  
31 member or members.

32 The external members may be rigid, semi-rigid, or flexible. Illustrative  
33 examples of the external members include a sheet material, a clamp, a ring, a tape, a  
34 wire (e.g., thin metal wire), an elastic band (e.g., rubber band, particularly a seamless

1 rubber band), a fabric thread, and the like. The external members may be fabricated by  
2 any suitable technique including for example machining and extrusion.

3 The external members may be taken off the substrate subsequent to the formation  
4 of the dip coated layer or left permanently in place on the substrate subsequent to the  
5 dip coating. In embodiments, the external members are positioned on the substrate by  
6 employing a non-fastener technique (i.e., without employing a fastener) such as by  
7 stretching the external member to fit around the substrate (e.g., the external member is  
8 an elastic band) or tightly wrapping the external member around the substrate (e.g., the  
9 external member is a wire or a thread and possibly tying together the ends of the wire or  
10 thread). In other embodiments, one or more fasteners couple the external members to  
11 the substrate. The term "fastener" includes for example adhesives, screws, bolts, and  
12 the like.

13 The term "level" indicates that the particular surface at issue (e.g., intermediate  
14 region) is parallel to the longitudinal axis.

15 In embodiments, the dip coated layer exhibits a substantially uniform thickness  
16 over the entire deposition region, particularly over the intermediate region. The phrase  
17 "substantially uniform thickness" indicates that the dry coating thickness over the  
18 deposition region varies by no more than about 10%, particularly no more than about  
19 5%, based on the largest thickness value of the dip coated layer.

20 The present method is believed to be based on the phenomenon of "capillary  
21 retention." When liquid is placed on a horizontal surface that is rough with a raised  
22 area and a depressed area, liquid will distribute more in the depressed areas per unit  
23 area due to surface tension of liquid and gravity. When such rough surface with liquid  
24 is positioned vertically, the liquid will flow downward. The contact angle based on the  
25 smooth surface is higher in the raised area than in the depressed area. Capillary force  
26 will exert driving force for the liquid to flow from the raised area to the depressed area.  
27 As a result, there is a higher percentage of liquid in the raised area flowing out. The  
28 most solution is retained in the depressed area, especially in the lower positions due to  
29 gravity. After the raised area is dip coated, the capillary force and gravity drag and  
30 deposit more of the coating solution in the surface area following the raised area. In the  
31 present invention, the external member functions as the raised area. Due to the  
32 presence of the external member, more of the coating solution is deposited in the dip  
33 coated layer over the intermediate region than would have occurred in the absence of  
34 the external member. Consequently, greater deposition of the coating solution over the  
35 intermediate region increases the coating thickness uniformity of the dip coated layer

1 over the intermediate region. For photoreceptors, greater coating thickness uniformity  
2 of the dip coated layer in the imaging area improves performance as compared with a  
3 photoreceptor exhibiting pronounced sloping of the dip coated layer in the imaging  
4 area.

5 When the substrate is oriented vertically for dip coating, the first end region is  
6 considered the top end region and the second end region is considered the bottom end  
7 region. The dip coated layer is formed over the deposition region in the recited order:  
8 (1) over the first external member/optional exposed first end region portion; (2) over  
9 the intermediate layer; and (3) over the second end region and/or optional second  
10 external member.

11 The phrase "dip coating" encompasses the following techniques to deposit  
12 layered material onto a substrate: moving the substrate into and out of the coating  
13 solution; raising and lowering the coating vessel to contact the coating solution with  
14 the substrate; positioning the substrate in a vessel containing the coating solution and  
15 then draining the coating solution from the vessel.

16 The substrate may be moved into and out of the solution at any suitable speed  
17 including the takeup speed indicated in Yashiki et al., U.S. Patent 4,610,942, the  
18 disclosure of which is hereby totally incorporated by reference. The dipping speed to  
19 contact the substrate with the coating solution may range for example from about 50  
20 to about 3,000 mm/min and may be a constant or changing value. The takeup speed  
21 to withdraw the substrate from the coating solution may range for example from about  
22 50 to about 500 mm/min and may be a constant or changing value. Any suitable  
23 dipping speed and takeup speed, including those discussed herein, can be used to  
24 deposit the desired layer or layers.

25 For the deposited layer or layers, each layer has a thickness ranging for example  
26 from about 0.05 to about 75 micrometers, and particularly from about 3 to about 40  
27 micrometers. Unless otherwise indicated, the disclosed thickness value for each layer  
28 is a dry thickness value.

29 The substrate can be formulated entirely of an electrically conductive material,  
30 or it can be an insulating material having an electrically conductive surface. The  
31 substrate can be opaque or substantially transparent and can comprise numerous  
32 suitable materials having the desired mechanical properties. The entire substrate can  
33 comprise the same material as that in the electrically conductive surface or the  
34 electrically conductive surface can merely be a coating on the substrate. Any suitable  
35 electrically conductive material can be employed. Typical electrically conductive



1 materials include metals like copper, brass, nickel, zinc, chromium, stainless steel;  
2 and conductive plastics and rubbers, aluminum, semitransparent aluminum, steel,  
3 cadmium, titanium, silver, gold, paper rendered conductive by the inclusion of a  
4 suitable material therein or through conditioning in a humid atmosphere to ensure the  
5 presence of sufficient water content to render the material conductive, indium, tin,  
6 metal oxides, including tin oxide and indium tin oxide, and the like. The substrate  
7 can vary in thickness over substantially wide ranges depending on its desired use.  
8 Generally, the conductive layer ranges in thickness from about 50 Angstroms to about  
9 30 micrometers, although the thickness can be outside of this range. When a flexible  
10 electrophotographic imaging member is desired, the substrate thickness typically is  
11 from about 0.015 mm to about 0.15 mm. When a rigid, hollow imaging member is  
12 desired, the substrate thickness is typically from about 0.5 mm to about 5 mm. The  
13 substrate can be fabricated from any other conventional material, including organic  
14 and inorganic materials. Typical substrate materials include insulating non-  
15 conducting materials such as various resins known for this purpose including  
16 polycarbonates, polyamides, polyurethanes, paper, glass, plastic, polyesters such as  
17 MYLAR® (available from DuPont) or MELINEX® 447 (available from ICI  
18 Americas, Inc.), and the like. If desired, a conductive substrate can be coated onto an  
19 insulating material. In addition, the substrate can comprise a metallized plastic, such  
20 as titanized or aluminized MYLAR®. The substrate can be flexible or rigid, and can  
21 have any number of configurations such as a cylindrical drum, an endless flexible  
22 belt, and the like.

23 The substrate and coating solution are described herein as being used in the  
24 fabrication of a photoreceptor. However, the present invention is not limited to the  
25 fabrication of a photoreceptor. In embodiments, the present invention uses other  
26 substrates and coating solutions not specifically described herein which are useful for  
27 other applications.

28 Any suitable coating solution can be used to form the layer or layers deposited  
29 over the substrate. In embodiments, the coating solution may comprise materials  
30 typically used for any layer of a photoreceptor including such layers as a charge  
31 barrier layer, an adhesive layer, a charge transport layer, and a charge generating  
32 layer, such materials and amounts thereof being illustrated for instance in U.S. Patent  
33 4,265,990, U.S. Patent 4,390,611, U.S. Patent 4,551,404, U.S. Patent 4,588,667, U.S.  
34 Patent 4,596,754, and U.S. Patent 4,797,337, the disclosures of which are totally  
35 incorporated by reference.

1 In embodiments, a coating solution may include the materials for a charge  
2 barrier layer including for example polymers such as polyvinylbutyral, epoxy resins,  
3 polyesters, polysiloxanes, polyamides, or polyurethanes. Materials for the charge  
4 barrier layer are disclosed in U.S. Patents 5,244,762 and 4,988,597, the disclosures of  
5 which are totally incorporated by reference.

6 The optional adhesive layer preferably has a dry thickness between about 0.001  
7 micrometer to about 0.2 micrometer. A typical adhesive layer includes film-forming  
8 polymers such as polyester, du Pont 49,000 resin (available from E. I. du Pont de  
9 Nemours & Co.). VITEL-PE100™ (available from Goodyear Rubber & Tire Co.),  
10 polyvinylbutyral, polyvinylpyrrolidone, polyurethane, polymethyl methacrylate, and  
11 the like. In embodiments, the same material can function as an adhesive layer and as  
12 a charge blocking layer.

13 In embodiments, a charge generating solution may be formed by dispersing a  
14 charge generating material selected from azo pigments such as Sudan Red, Dian Blue,  
15 Janus Green B, and the like; quinone pigments such as Algol Yellow, Pyrene  
16 Quinone, Indanthrene Brilliant Violet RRP, and the like; quinocyanine pigments;  
17 perylene pigments; indigo pigments such as indigo, thioindigo, and the like;  
18 bisbenzoimidazole pigments such as Indofast Orange toner, and the like;  
19 phthalocyanine pigments such as copper phthalocyanine, aluminochloro-  
20 phthalocyanine, and the like; quinacridone pigments; or azulene compounds in a  
21 binder resin such as polyester, polystyrene, polyvinyl butyral, polyvinyl pyrrolidone,  
22 methyl cellulose, polyacrylates, cellulose esters, and the like. A representative charge  
23 generating solution comprises: 2% by weight hydroxy gallium phthalocyanine; 1%  
24 by weight terpolymer of vinyl acetate, vinyl chloride, and maleic acid; and 97% by  
25 weight cyclohexanone.

26 In embodiments, a charge transport solution may be formed by dissolving a  
27 charge transport material selected from compounds having in the main chain or the  
28 side chain a polycyclic aromatic ring such as anthracene, pyrene, phenanthrene,  
29 coronene, and the like, or a nitrogen-containing hetero ring such as indole, carbazole,  
30 oxazole, isoxazole, thiazole, imidazole, pyrazole, oxadiazole, pyrazoline, thiadiazole,  
31 triazole, and the like, and hydrazone compounds in a resin having a film-forming  
32 property. Such resins may include polycarbonate, polymethacrylates, polyarylate,  
33 polystyrene, polyester, polysulfone, styrene-acrylonitrile copolymer, styrene-methyl  
34 methacrylate copolymer, and the like. An illustrative charge transport solution has the  
35 following composition: 10% by weight N,N'-diphenyl-N,N'-bis(3-methylphenyl)-

1 (1,1'-biphenyl)-4,4'diamine; 14% by weight poly(4,4'-diphenyl-1,1'-cyclohexane  
2 carbonate) (400 molecular weight); 57% by weight tetrahydrofuran; and 19% by  
3 weight monochlorobenzene.

4 A coating solution may also contain a liquid medium, preferably an organic  
5 liquid medium, such as one or more of the following: tetrahydrofuran,  
6 monochlorobenzene, and cyclohexanone.

7 After all the desired layers are coated onto the substrate, the coated layers may  
8 be subjected to elevated drying temperatures such as from about 100 to about 160°C  
9 for about 0.2 to about 2 hours.

10 The invention will now be described in detail with respect to specific preferred  
11 embodiments thereof, it being understood that these examples are intended to be  
12 illustrative only and the invention is not intended to be limited to the materials,  
13 conditions, or process parameters recited herein. All percentages and parts are by  
14 weight unless otherwise indicated.

#### 15 EXAMPLE 1

16 A commercially available endless rubber band of the following dimensions was  
17 used: about 1 mm thickness, about 2 mm width and about 150 mm full length. The  
18 substrate was a rigid cylindrical drum of about 30 mm in diameter and about 350 mm  
19 in length. The rubber band was wrapped around the drum twice with the two loops  
20 closely spaced to each other. The lower edge of the rubber band loops was about 5-10  
21 mm from the top edge of the drum. The drum was then inserted into the coating  
22 solution until the surface of the solution reached the 8-9 mm from the top edge of the  
23 drum. The solution was about 300 centipoise in viscosity and about 25% in its solids  
24 content. The drum was pulled out of the solution steadily at about 150 mm per  
25 minute. After the drum was completely pulled out of the solution, it was removed  
26 from the dip coating apparatus and placed in a heated oven at about 130 degrees C for  
27 30 minutes to remove solvents. A commercial optical gauge was used to measure the  
28 thickness of the dried coating. The average thickness was calculated at about 30 mm  
29 from the top edge of the drum. Another average thickness was calculated in the major  
30 part of the drum between 100 and 300 mm from the top edge. The difference was  
31 used as the sloping. The sloping was about 1.78 micrometers.  
32  
33  
34

## COMPARATIVE EXAMPLE 1

The procedures of Example 1 were followed except that no rubber band was used. The sloping about 2.39 micrometers. Thus, the improvement of sloping exhibited by Example 1 with a rubber band was about 0.61 micrometers or about 25% compared with Comparative Example 1.

## EXAMPLE 2

A commercially available aluminum tape was used. The tape had a thickness of about 125 micrometers. The substrate was a rigid cylindrical drum of about 30 mm in diameter and about 350 mm in length. The tape was wrapped around the drum once. The lower edge of the tape was about 10-11 mm from the top edge of the drum. The upper edge of the tape was about 1-2 mm from the top edge of the drum. The drum was then inserted into the coating solution until the surface of the solution reached about 5-10 mm from the top edge of the drum. The solution was about 300 centipoise in viscosity and about 25% in its solids content. The drum was pulled out of the solution steadily at about 150 mm per minute. After the drum was completely pulled out of the solution, it was removed from the dip coating apparatus and placed in a heated oven at about 130 degrees C for 30 minutes to remove solvents. A commercial optical gauge was used to measure the thickness of the dried coating. The average thickness was calculated at about 30 mm from the top edge of the drum. Another average thickness was calculated in the major part of the drum between 100 and 300 mm from the top of the edge. The difference was used as the sloping. The sloping was 1.95 micrometers.

## COMPARATIVE EXAMPLE 2

The procedures of Example 2 were followed except that no aluminum tape was used. The sloping was about 2.39 micrometers. Thus, the improvement of sloping exhibited by Example 2 with the aluminum tape was about 0.44 micrometers or about 18% compared with Comparative Example 2.

Other modifications of the present invention may occur to those skilled in the art based upon a reading of the present disclosure and these modifications are intended to be included within the scope of the present invention.